

Technical Data Sheet (ISO)

ABS(Acrylonitrile Butadiene Styrene)

ABS 750SH

Features	Easy flow, white, medium impact strength
Applications	Electronics, Household appliances, Miscellaneous goods

Physical	Test Method	Value
Specific gravity	ISO 1183	1.04
Melt Flow Index (220°C, 10kg)	ISO 1133	35 g/10min
Water absorption	ISO 62	- %
Mold Shrinkage	ISO 294-4	0.5 ~ 0.8 %

Mechanical	Test Method	Value
Tensile Strength(at yield)	ISO 527	44 Mpa
Elongation(at break)	ISO 527	17 %
Flexural Strength	ISO 178	69 MPa
Flexural Modulus	ISO 178	2,400 Mpa
Izod Impact Strength(23°C)	ISO 180/1A	23 KJ/m ²
Charpy Impact Strength(23°C)	ISO 179/1eA	24 KJ/m ²
Rockwell Hardness(R scale)	ISO 2039-2	108

Thermal	Test Method	Value
Heat Deflection Temperature(1.8Mpa, Unannealed)	ISO 75-2	80 °C
Heat Deflection Temperature(0.45Mpa, Unannealed)	ISO 75-2	91 °C
Vicat Softening Temperature(B50)	ISO 306	95 °C

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.