

Technical Data Sheet (ISO)

ABS(Acrylonitrile Butadiene Styrene)

ABS 775

Features Refrigerator sheet, High impact resistance
Applications Refrigerator inner case, door liner (Cyclepentane foaming agent use)

Physical	Test Method	Value
Specific gravity	ISO 1183	1.04
Melt Flow Index (220°C, 10kg)	ISO 1133	5 g/10min
Water absorption	ISO 62	- %
Mold Shrinkage	ISO 294-4	0.5 ~ 0.8 %

Mechanical	Test Method	Value
Tensile Strength(at yield)	ISO 527	43 Mpa
Elongation(at break)	ISO 527	27 %
Flexural Strength	ISO 178	63 MPa
Flexural Modulus	ISO 178	2,350 Mpa
Izod Impact Strength(23°C)	ISO 180/1A	36 KJ/m ²
Charpy Impact Strength(23°C)	ISO 179/1eA	37 KJ/m ²
Rockwell Hardness(R scale)	ISO 2039-2	105

Thermal	Test Method	Value
Heat Deflection Temperature(1.8Mpa, Unannealed)	ISO 75-2	82 °C
Heat Deflection Temperature(0.45Mpa, Unannealed)	ISO 75-2	93 °C
Vicat Softening Temperature(B50)	ISO 306	97 °C

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.