



**Technical Data Sheet** 

## EPS(Expandable Polystyrene) SEPS N20 SC

## FeaturesSelf-extinguish, High productivity(N20 SC is 70% faster than the N20)ApplicationsInsulation board, Construction Materials, Packing materials

Typical Properties	Test Method	Value
Bead Size	Kumho	0.6 ~ 0.9 mm
Expandability <sup>1)</sup>	Kumho	75 multiple
Blowing Agent	Kumho	5.5 %
Normal Molded Density Range	Kumho	20 ~ 25 kg/m <sup>3</sup>

1) Expandability : Expansion multiple after 5 minutes in steam chamber (0.3 kgf/cm<sup>2</sup> steam pressure)

echanical Properties	Test Method	Value
Density	KS M 3808	20 kg/m <sup>3</sup>
Primary Thermal Conductivity	KS M 3808	0.038 W/mk
Flexural Demolition Load	KS M 3808	27 N
Compression Strength	KS M 3808	10 N/cm <sup>2</sup>
Amount of Water Absorption	KS M 3808	0.3g /100cm <sup>2</sup>
Combustibility	KS M 3808	2.0 sec
		20 mm

1) KS M 3808 : The Korean Industrial Standard

Flammability	Test Method	Value
UL	UL 94	HF-1(Approval)
	UL 723	Approval

## Notes

These are just typical properties, not specifications. Users should confirm results by their own test.