

Technical Data Sheet (ASTM)

ABS(Acrylonitrile Butadiene Styrene)

ABS 728

Features

General high gloss

Applications

Products demanding for gloss: Sweeper, Wassing machine cover etc

Physical	Test Method	Value
Density	ASTM D792	1.04 g/cm ³
Melt Flow Index (220°C, 10kg)	ASTM D1238	40 g/10min
Melt Flow Index (200°C, 21.6kg)	ASTM D1238	60 g/10min
Mold Shrinkage	ASTM D955	0.5 ~ 0.8 %
Water absorption	ASTM D570	- %
Mechanical	Test Method	Value
Tensile Strength	ASTM D638	470 kgf/cm ²
Elongation	ASTM D638	20 %
Flexural Strength	ASTM D790	650 kgf/cm ²
Flexural Modulus	ASTM D790	22,000 kgf/cm ²
Izod Impact Strength(3.2mm, 23°C)	ASTM D256	25 kgf-cm/cm
Izod Impact Strength(6.4mm, 23°C)	ASTM D256	20 kgf-cm/cm
Rockwell Hardness(R scale)	ASTM D785	108
Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	86 °C
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	96 °C
Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.