

Technical Data Sheet

**ABS & PC Alloy (Engineering Plastics)
HAC 8244**

Features High Impact Strength, Plating
Applications Automobile parts(Panel, Mesh bumpers), Helmets, Plating parts, etc

Physical	Test Method	Value
Density	ASTM D792	1.12 g/cm ³
Melt Flow Index (230°C, 21.6kg)	ASTM D1238	40 g/10min
Mold Shrinkage	ASTM D955	0.4 ~ 0.6 %
Water absorption	ASTM D570	- %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	440 kg/cm ²
Elongation	ASTM D638	110 %
Flexural Strength	ASTM D790	600 kg/cm ²
Flexural Modulus	ASTM D790	17,000 kg/cm ²
Izod Impact Strength(6.4mm)	ASTM D256	50 kg-cm/cm
Rockwell Hardness(R scale)	ASTM D785	100

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	100 °C (212) (°F)
Vicat Softening Temperature(5kg, 50°C/h)	ASTM D1525	116 °C (241) (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.