

## KUMHO PETROCHEMICAL

KUMHO BLDG 57, 15TH &amp; 16TH FL, 57 SHINMMUNRO, 1-KA, CHONGNO-KU, SEOUL 110-061 KR

## HAC 8250NH

Acrylonitrile Butadiene Styrene/Polycarbonate (ABS/PC), furnished as pellets

| Color | Min Thk<br>(mm) | Flame<br>Class | HWI | HAI | RTI<br>Elec | RTI<br>Imp | RTI<br>Str |
|-------|-----------------|----------------|-----|-----|-------------|------------|------------|
| ALL   | 1.5             | V-0            | 3   | 0   | 60          | 60         | 60         |
|       | 2.2             | V-0, 5VA       | 2   | 0   | 60          | 60         | 60         |
|       | 3.0             | V-0, 5VA       | 1   | 0   | 60          | 60         | 60         |

Comparative Tracking Index (CTI): 2

Dimensional Stability (%): -

High-Voltage Arc Tracking Rate (HVTR): 4

High Volt, Low Current Arc Resis (D495): 7

Dielectric Strength (kV/mm): -

Volume Resistivity (10<sup>X</sup> ohm-cm): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1987-05-04

Last Revised: 2003-10-24

Underwriters Laboratories Inc®



## IEC and ISO Test Methods

| Test Name                      | Test Method     | Units             | Thickness<br>Tested (mm) | Value          |
|--------------------------------|-----------------|-------------------|--------------------------|----------------|
| IEC Flammability               | IEC 60695-11-10 | Class (color)     | 1.5                      | V-0 (ALL)      |
|                                |                 |                   | 2.2                      | V-0, 5VA (ALL) |
|                                |                 |                   | 3.0                      | V-0, 5VA (ALL) |
| Glow-Wire Flammability (GWFI)  | IEC 60695-2-12  | C                 | -                        | -              |
| Glow-Wire Ignition (GWIT)      | IEC 60695-2-13  | C                 | -                        | -              |
| IEC Comparative Tracking Index | IEC 60112       | Volts (Max)       | -                        | -              |
| IEC Ball Pressure              | IEC 60695-10-2  | C                 | -                        | -              |
| ISO Heat Deflection (1.80 MPa) | ISO 75-2        | C                 | -                        | -              |
| ISO Tensile Strength           | ISO 527-2       | MPa               | -                        | -              |
| ISO Flexural Strength          | ISO 178         | MPa               | -                        | -              |
| ISO Tensile Impact             | ISO 8256        | kJ/m <sup>2</sup> | -                        | -              |
| ISO Izod Impact                | ISO 180         | kJ/m <sup>2</sup> | -                        | -              |
| ISO Charpy Impact              | ISO 179-2       | kJ/m <sup>2</sup> | -                        | -              |

Underwriters Laboratories Inc®